

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-328631

(43)Date of publication of application : 22.12.1997

(51)Int.Cl. C09C 3/12
C08K 3/34
C08K 9/06
C08L 21/00
C09C 1/28

(21)Application number : 09-053746 (71)Applicant : DEGUSSA AG
(22)Date of filing : 10.03.1997 (72)Inventor : BARTHEL THOMAS
GOERL UDO
PARKHOUSE ALAN
EICHENAUER KURT

(30)Priority


Priority	96 19609619	Priority	12.03.1996	Priority	DE
number :		date :		country :	

(54) GRANULE HAVING SILICATE FILLER MODIFIED WITH ORGANOSILICON COMPOUND AS BASE, GENERATING LOW DUST AND HAVING GOOD DISPERSING ABILITY, ITS PRODUCTION AND RUBBER MIXTURE CONTAINING THE SAME

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain the granules having high preservation stability and a low dust content, excellent in compatibility with rubber mixture by using a precipitated silicate filler modified with an organic silicon compound as a base.

SOLUTION: The objective granules are produced by precipitation and using silicate filler modified with an organic silicon compound expressed by formula I [B is SCN, SH, Cl or NH₂ when (q) is 2, or Sx when (q)=2; R and R₁ are each a 1-4C alkyl; R is an additional H; (n) is 0, 1 or 2; (y) is 0-19; (z) and (i) are each 1; (x) is 2-8 and the reaction rate of an alkoxy group is given by an integration ratio of signals obtained by using a ¹³C-NMR spectrometer and expressed by formula II] as a base. This production of the subject granules is to prepare an aqueous suspension of the silicate filler having pH1-5, spray or inject from a nozzle the suspension and one or more of compounds of formula I with air into a fluidized bed, take out wet granules modified with the organic silicon compound and having a predetermined granule size, dry the granules, separate a fine part of the



I

$$2 \leq R_1 \frac{(C_1H_2)_x}{(C_1H_2)_y} \leq 0.4 \text{ (} q=2 \text{ の場合) } ; \leq 0.15 \text{ (} q=1 \text{ の場合)}$$

$$2 \leq R_1 \frac{R-(C_1H_2)_x}{(C_1H_2)_y} \leq 0.4 \text{ (} q=2 \text{ の場合) } ; \leq 0.15 \text{ (} q=1 \text{ の場合)}$$

II

granules, feed back the granules into the fluidized bed and adjust to pH6-7.5.

LEGAL STATUS

[Date of request for examination] 21.01.2004

[Date of sending the examiner's decision
of rejection]

[Kind of final disposal of application
other than the examiner's decision of
rejection or application converted
registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's
decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]